

#### **Technical Data sheet**

### Sheating





Our asphalt-coated products are composed of interlocking cellulose fibres bonded together by heat, pressure and premium bitumen emulsion.

The density of this material has been specified to provide an optimum combination of board strength and insulation value.

The acoustical insulation panels of MSL are composite panels combining the high-performance of fibreboard panels to the EPS .

The SONOclimat® panels are distinguished by their strength, superior physical properties and represent an excellent choice for insulation and acoustical needs for your exterior walls.

Our continuous quality control in the manufacturing process and the judicious choice of selected raw material provide our customers a superior quality product.

# Advanced R4 Insulation Panel

Properties	Requirements	Results
Density (voluminal mass) Fibreboard Expanded Polystyrene	ASTM D-1037 ASTM-3575	16 lb / ft³ 256 kg / m³ 1,3 lb / ft³ 20.82 kg / m³
Transverse load at rupture Fibreboard	ASTM C-209	17 lb 7.7 kg
Tensile strength parallel to surface Fibreboard	ASTM C-209	330 lb/in² 2275 kPa
Water absorption Fibreboard Expanded Polystyrene	ASTM C-209 D570	2,3% 0,8%
Linear expansion Fibreboard	ASTM D-1037	0,08%
Compressive strength (10% deform Fibreboard Expanded Polystyrene	nation) ASTM C-165 ASTM D-1621	Over 35 lb/in² (min) (Over 241 kPa (min)) 18.21 lb/in² (125.20 kPa)
Water vapour permeability SONOclimat R4 perms (290 ng)		ASTM E-965.08
Air permeability Fibreboard	ASTM E-2178-03	1,058 L/(s.m²) to 75Pa
Nail pull through resistance Fibreboard	ASTM D-1037	41 lbs 18.6 kg
"R" Factor SONOclimat®	ASTM C-518-04	4.00 oF ft <sup>2</sup> hr/BTU



infoplus@mslfibre.com • www.mslfibre.com

For information: contact our customer service 1 800 561.4279



















Technical Data sheet (continued)

## Sheating



### Advanced R4 Insulation Panel

Dimensions 4' X 8' (1.22 m x 2.44 m)

4' x 9' (1.22 m x 2.75 m) 4' x 9.2' ( 1.22 m x 2.79 m)

Thickness 1 1/8' ( 28.57 mm)

The information on this Technical Data sheet is based upon data considered to be true and accurate, based on laboratory tests and production measurements, and is offered solely for the user's consideration, investigation and verification. Nothing contained herein is representative of a warranty or guarantee for which the manufacturer can be held legally responsible. The manufacturer does not assume any responsibility for any misrepresentation or assumptions

the reader may formulate.





















