

#### **Technical Data sheet**

### Coated6s

## **Sheating**





This product conforms to all requirements of CAN / ULC-S706-09 and ASTM C208.

The density of this material has been specified to provide an optimum combination of board strength and insulating value.

Our roofing products are produced and designed with consideration for environmental responsibility and sustainability, manufactured in facilities that comply with the most stringent government environmental regulations, and can therefore be a part of any "green" construction project.





# Wood fibre standard coated

Standard Limits **Nominal Value Properties** ≥15 lb / ft<sup>3</sup> Density Transverse load at rupture Min 48N ≥ 48N Min 10,8 lbF ≥ 10,8 lbF Min 24 KPa ≥ 24 KPa Tensile strength perpendicular to surface Min 3,48 psi ≥ 3,48 psi ≥ 1000 KPa Tensile strength parallel Min 1000 KPa to surface Min 145 psi ≥ 145 psi Max 7 % ≤ 7% Water absorption Max 0,5 % ≤ 0,5% Linear expansion Min 100 KPa ≥ 100 KPa Compressive strength ≥ 14,5 psi Min 14,5 psi (10% deformation) "R" factor / inch (1") Min 0,41 [(m<sup>2</sup> • K)/w] 2,90 N/D Permeability to the steam 18,7 perms

	A CONTRACTOR OF THE PARTY OF TH
Dimension	4' X 8'
Thickness	7/16" (11 mm)

The information on this Technical Data sheet is based upon data considered to be true and accurate, based on laboratory tests and production measurements, and is offered solely for the user's consideration, investigation and verification. Nothing contained herein is representative of a warranty or guarantee for which the manufacturer can be held legally responsible. The manufacturer does not assume any responsibility for any misrepresentation or assumptions the reader may formulate.



infoplus@materiauxspecl.com • www.materiauxspecl.com

For information: contact our customer service 1 800 561.4279















Product No.



#### **Technical Data sheet**

## Coated6s

# **Sheating**



Our Wood Fibre Roof Insulation Panels are composed of interlocking cellulose fibres bonded together by heat, pressure and premium bitumen emulsion.

This product conforms to all requirements of CAN / ULC-S706-09 and ASTM C208.

The density of this material has been specified to provide an optimum combination of board strength and insulating value.

Our roofing products are produced and designed with consideration for environmental responsibility and sustainability, manufactured in facilities that comply with the most stringent government environmental regulations, and can therefore be a part of any "green" construction project.





# Wood fibre standard coated

	S	894
Properties	Standard Limits	Nominal Value
Density		≥15 lb / ft³
Transverse load at rupture	Min 48N Min 10,8 lbF	≥ 48N ≥ 10,8 lbF
Tensile strength perpendicular to surface	Min 24 KPa Min 3,48 psi	≥ 24 KPa ≥ 3,48 psi
Tensile strength parallel to surface	Min 1000 KPa Min 145 psi	≥ 1000 KPa ≥ 145 psi
Water absorption	Max 7 %	≤ 7%
Linear expansion	Max 0,5 %	≤ 0,5%
Compressive strength (10% deformation)	Min 100 KPa Min 14,5 psi	≥ 100 KPa ≥ 14,5 psi
"R" factor / inch (1")	Min 0,41 [(m² • K)/w]	2,90
Permeability to the steam	N/D	18,7 perms

the latest	and the second of the second of the second
Dimension	4' X 9'
Thickness	7/16" (11 mm)

The information on this Technical Data sheet is based upon data considered to be true and accurate, based on laboratory tests and production measurements, and is offered solely for the user's consideration, investigation and verification. Nothing contained herein is representative of a warranty or guarantee for which the manufacturer can be held legally responsible. The manufacturer does not assume any responsibility for any misrepresentation or assumptions the reader may formulate.



infoplus@materiauxspecl.com • www.materiauxspecl.com

For information: contact our customer service 1 800 561.4279

















Product No.

004



#### **Technical Data sheet**

### Coated6s

# Sheating



Our Wood Fibre Roof Insulation Panels are composed of interlocking cellulose fibres bonded together by heat, pressure and premium bitumen emulsion.

This product conforms to all requirements of CAN / ULC-S706-09 and ASTM C208.

The density of this material has been specified to provide an optimum combination of board strength and insulating value.

Our roofing products are produced and designed with consideration for environmental responsibility and sustainability, manufactured in facilities that comply with the most stringent government environmental regulations, and can therefore be a part of any "green" construction project.







## High Performance Wood fibre standard coated

 Product No.

 Standard Coated

 Properties
 Standard Limits
 Nominal Value

 Density
 ≥ 16 lb / ft³

 Transverse load at rupture
 Min 62N
 ≥ 62N

 Min 14 lbE
 > 14 lbE

Density	-	≥16 lb / tt³
Transverse load at rupture	Min 62N Min 14 lbF	≥ 62N ≥ 14 lbF
Tensile strength perpendicular to surface	Min 24 KPa Min 3,48 psi	≥ 24 KPa ≥ 3,48 psi
Tensile strength parallel to surface	Min 1000 KPa Min 145 psi	≥ 1000 KPa ≥ 145 psi
Water absorption	Max 7 %	≤ 7%
Linear expansion	Max 0,5 %	≤ 0,5%
Compressive strength (10% deformation)	Min 100 KPa Min 14,5 psi	≥ 100 KPa ≥ 14,5 psi
"R" factor / inch (1")	Min 0,41 [(m² • K)/w]	2,90
Permeability to the steam	N/D	18,7 perms
Retention (on common nail of 2")	N/D	41 lb 182 N

	The state of the s
Dimension	4' X 9'
Thickness	1/2" (12.7 mm)

The information on this Technical Data sheet is based upon data considered to be true and accurate, based on laboratory tests and production measurements, and is offered solely for the user's consideration, investigation and verification. Nothing contained herein is representative of a warranty or guarantee for which the manufacturer can be held legally responsible. The manufacturer does not assume any responsibility for any misrepresentation or assumptions the reader may formulate.

infoplus@materiauxspecl.com • www.materiauxspecl.com

For information: contact our customer service 1 800 561.4279

















